

PROTECT CB 101

Cementitious Waterproofing Coat (Two Components)

Protect CB 101 is a cement-based, two-component polymer-modified waterproofing slurry. The product provides a flexible layer which can be used for internal waterproofing, crack sealing, and as a repairing mortar for cement and concrete surfaces.

SCOPE OF USE

- On concrete surfaces and cement plasters
- Swimming pools and waterproofing of drinking water tanks and reservoirs
- For vertical and horizontal applications
- Bridges & sea walls
- Waterproofing basements and cellars
- Waterproofing of terraces, roofs, and balconies
- Water treatment facilities
- Sewage treatment facilities including concrete tanks
- Bathrooms, toilets, and kitchens

ADVANTAGES

- Can be applied on damp surfaces
- Cracks-bridging ability & good substrate adhesion
- Non-toxic, ideal for confined areas & drinking water
- Flexible, cementitious, water-impermeable
- Provides a long-lasting waterproofing layer
- Resistant to abrasion, frost, and salt
- Non-corrosive to steel/iron & over-paintable
- Resistant to salt water, grease, and oil

TECHNICAL PROPERTIES

COLOR	Grey and white
WATER IMPERMEABILITY (POSITIVE / NEGATIVE)	5 bar (positive) / 3 bar (negative)
APPLICATION TEMPERATURE	Between +5°C and +35°C
AVERAGE CONSUMPTION	1.8kg/m ² at 1mm WFT thickness
RECOATING TIME / FULL DRYING TIME (+23°C)	5 - 10 hours / 24 - 48 hours

APPLICATION GUIDE

1. Surface Preparation

Concrete surfaces should be clean, sound, and free from oil, grease, cement laitance, and all loosely adhering particles. The surface should be in a saturated surface dry condition. Weak parts of concrete should be repaired; loose texture should be scraped. Any cracks and fractures on the surface should be carefully repaired with repair mortars. After the surface is ready, the primer should be applied. In open environments such as terraces, corners must be chamfered at a 45° angle (horizontally or vertically) to prepare for insulation.

2. Product Preparation

Put the liquid component into the mixing bowl and slowly pour the powder component into the liquid while mixing with a low-speed mixer without adding water until there are no lumps. Wait for 5 minutes until it becomes viscous, then mix for 20 - 30 seconds and apply in one direction and at corners with a brush.

3. Application Process

Application should start no later than 5 hours after primer (in case high absorbent substrates) application. Apply to the substrate in two coats by brush, roller, or spraying. The application of each layer should be perpendicular to the previous one and completed at one time. The prepared mortar should be consumed within 30 minutes. Do not add water to the mixture externally. The powder component must always be added to the liquid component. Wait at least 5 hours between coats. Drying time may be prolonged in low temperature and high humidity environments.

PACKAGING & STORAGE

- **Packaging:** Original reference: 20 kg (15 Powder, 5 Liquid).
- **Storage Conditions:** Protect CB 101 should be stored at temperatures between 10°C and 35°C in closed packaging. The storage area should be dry, well-ventilated, and away from any source of heat or direct sunlight.
- **Shelf Life:** 12 months from the date of manufacture.
- **Support:** If these requirements are breached, contact the Technical Department of Pro-tec for assistance.

HEALTH, SAFETY & CAUTIONS

Protect CB 101 is non-toxic, non-flammable, water-based, and does not cause any health damage. However, always take care and adhere to standard safety precautions.

- **Protective Gear:** Wear protective clothing, such as gloves and goggles. Apply in a well-ventilated area, and avoid dust inhaling.
- **Skin & Eye Contact:** The product contains cement powders which release alkalis when mixed with water. Splashes on the skin should be washed away with soap and water immediately. In case of contact with eyes, wash thoroughly with clean water.
- **Ingestion:** If swallowed, do not induce vomiting. Seek medical attention.

PRO-TEC

Trust our chemistry

Disclaimer: Pro-Tec makes every effort to ensure that any advice, suggestions, or information it provides is reliable and accurate. It cannot assume any direct or indirect liability arising from the use of its goods since it has no direct or continuous control over where or how its products are used, whether or not in line with any advice, specification, suggestion, or information provided by us. Pro-Tec has the right, at its discretion, to alter any of the parameters included in the technical data sheets without previous notice. Hard copies of the technical data sheets are printed once or twice a year, while our technical data sheets are constantly updated as a result of R&D advancements and fresh third-party testing; please visit our website for the most recent updates.

Note: The information included on this Technical Data Sheet is the sole property of Pro-Tec. The unauthorized disclosure, use, dissemination, or copying (either whole or partial) of this data sheet or any information it contains is prohibited and subject to legal pursuit.