

PRO-TEC

Trust our chemistry

Tec P silk Mut

Acrylic vinyl Silk (plastic) Washable, half gloss

This product is an interior emulsion paint. Based on acrylic copolymer emulsion.

SCOPE OF USE

■ Cement plaster, concrete, block work, rendered surfaces, gypsum board etc.

ADVANTAGES

■ Excellent penetration into the substrate there by providing the best adhesion. Offers best protection against alkali attack.

TECHNICAL DATA

This product's technical values are not printed on the supplied packaging and are pending confirmation from PRO-TEC's Technical / R&D Department based on lab testing. Do not publish or distribute until verified and completed.

Solids by volume	30 ± 2 volume% Theoretical
Specific gravity	1.2 Theoretical Only for white colour
Nozzle tip	0.021-0.027"
Spray angle degrees	65-800

APPLICATION GUIDE

1. Surface Preparation

The surface to be treated must be clean, dry, and free from leakage, loose oil paint, dirt, dust, grease, oils, soap, wax and any other contaminants. Remove any peeling paint and sand the area smooth, feathering the edges with adequate sandpaper.

2. Substrate Condition

New plaster or masonry surfaces must be allowed to cure prior to application, and the surface plaster must be allowed to dry in good condition before the putty is applied.

3. Repairs Before Application

Repair any cracks in base elements, leakage or previous surface problems before painting. Ensure non-structural cracks are filled with cement filler before proceeding, and wash putty depths/cracked areas thoroughly with drinking water as needed.

4. Finishing

Typical recommended range

Cleaning of painting tools

Typical recommended range

Dry film thickness 30 60 µm Wet film thickness 117 200 µm Film thickness will vary and is calculated as average.

Theoretical spreading rate 7 - 6 m²/l

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

Maximum spread rate per coat is obtained at minimum dry film thickness and vice versa.

Thinner

Water

Dilution

Maximum 10 %

Conditions during application

The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying.

Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

I. Recommended data given is, for recoating with the same generic type of paint.

PACKAGING & STORAGE

Supplied in 4 Land 18L packaging.

HEALTH, SAFETY & CAUTIONS

Water-based acrylic putty; avoid prolonged skin/eye contact and ensure adequate ventilation during sanding.

- Avoid prolonged contact with eyes and skin.
- Use appropriate PPE (gloves, eye protection) during application.
- Ensure good ventilation during use, especially in confined interior spaces.
- Refer to the product Material Safety Data Sheet (MSDS) for complete health and safety guidance.
- Keep out of reach of children. Store away from sources of heat and ignition.

PRO-TEC

Trust our chemistry

Disclaimer:

Pro-Tec makes every effort to ensure that any advice, suggestions, or information it provides is reliable and accurate. It cannot assume any direct or indirect liability arising from the use of its goods since it has no direct or continuous control over where or how its products are used, whether or not in line with any advice, specification, suggestion, or information provided by us. Pro-Tec has the right, at its discretion, to alter any of the parameters included in the technical data sheets without previous notice. Hard copies of the technical data sheets are printed once or twice a year, while our technical data sheets are constantly updated as a result of R&D advancements and fresh third-party testing; please visit our website for the most recent updates.

Note: The information included on this Technical Data Sheet is the sole property of Pro-Tec. The unauthorized disclosure, use, dissemination, or copying (either whole or partial) of this data sheet or any information it contains is prohibited and subject to legal pursuit.